5

10



ABSTRACT OF DISCLOSURE

Poorly adherent layers such as silicon nitride and silicon dioxide exhibit improved adhesion to copper member by providing an intervening germanium-containing layer. The germanium-containing layer is copper germanide, germanium oxide, germanium nitride or combinations thereof. The germanium-containing layer enhances the adhesion such that the poorly adherent layer is less susceptible to delamination from the copper member.